

Technical Data Sheet



OPAZIL® ACK는 몬모릴로나이트를 기본으로 하여 화학적 변화시킨
층상 규산염 광물이고 당사의 DIN EN ISO 9001을 준수한다.

물리적특성 (평균 값)	단위	OPAZIL® ACK
형상	-	Powder
백색도 (Method of analysis OP 0007*)	%	Min, 30
수분 (Method of analysis OP 0009*)	%	Min, 11
PH (Method of analysis AL 0118*)	-	9.0 ~ 11.0
접성 (Method of analysis OP 005*)	mPas	100 ~ 500
Wet sieve residues > 53μ (Method of analysis OP 0010*)	%	Max, 0.1
Bulk density (Method of analysis OP 0003*)	g/l	Approx 600

클라리언트코리아(주)

경북 포항시 남구 대송면

철강로 492 번길 78

www.clariantimk.com

www.clariant.com

COPYRIGHT ©
CLARIANT INTERNATIONAL LTD 2012

EDITION
July 2017

This information corresponds to the present state of our knowledge and is intended as a general description of our products and their possible applications. Clariant makes no warranties, express or implied, as to the information's accuracy, adequacy, sufficiency or freedom from defect and assumes no liability in connection with any use of this information. Any user of this product is responsible for determining the suitability of Clariant's products for its particular application. * Nothing included in this information waives any of Clariant's General Terms and Conditions of Sale, which control unless it agrees otherwise in writing. Any existing intellectual/industrial property rights must be observed. Due to possible changes in our products and applicable national and international regulations and laws, the status of our products could change. Material Safety Data Sheets providing safety precautions, that should be observed when handling or storing Clariant products, are available upon request and are provided in compliance with applicable law. You should obtain and review the applicable Material Safety Data Sheet information before handling any of these products. For additional information, please contact Clariant.

* For sales to customers located within the United States and Canada the following applies in addition: NO EXPRESS OR IMPLIED WARRANTY IS MADE OF THE MERCHANTABILITY, SUITABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OTHERWISE OF ANY PRODUCT OR SERVICE.

All information in this publication is in accordance with our present and knowledge. However, since we have no influence on the way in which our products are treated and used, we cannot take any responsibility in this respect. The user must assume responsibility himself for checking whether the products are suitable for the purpose and use proposed by him. All existing proprietary rights, laws and regulations shall be observed.

*) Methods of Clariant IMK, following DIN standards is available upon request
© Trademark registered in many countries and owned by Clariant
© 2012 Clariant International Ltd, Rothausstrasse 61, 4132 Muttenz, Switzerland

